

# SIGMAZINC 109 HS

(SIGMARITE HS ZINC PRIMER)

4 pages

March 2007  
Revision of May 2006

<b>DESCRIPTION</b>	two component high solids polyamide adduct cured zinc epoxy primer
<b>PRINCIPAL CHARACTERISTICS</b>	<ul style="list-style-type: none"> <li>– designed as a system primer for various paint systems</li> <li>– excellent anticorrosive properties</li> <li>– quick drying, can be overcoated after a short interval</li> <li>– can serve as a holding primer for various maintenance systems for a total repair</li> <li>– very good primer for systems with high solids epoxy buildcoats</li> <li>– complies with SSPC-Paint 20 and ISO 12944.5</li> </ul>
<b>COLORS AND GLOSS</b>	reddish grey - flat
<b>BASIC DATA AT 68°F</b>	(8.25 lb/US gal = 1 g/cm <sup>3</sup> ; 40.7 ft <sup>2</sup> /US gal = 1 m <sup>2</sup> /l) (data for mixed product)
Mass density	23.37 lbs/gal (2.8 g/cm <sup>3</sup> )
Solids content	66 ± 2%
VOC (supplied - EPA 24)	max. 106 g/kg (Directive 1999/13/EC, SED) max. 2.5 lb/gal (approx. 299 g/l)
Recommended dry film thickness	2.4 - 6 mils (60 - 150 µm) depending on system
Theoretical spreading rate	447 ft <sup>2</sup> /gal (11.0 m <sup>2</sup> /l) for 2.4 mils (60 µm) *
Touch dry after	2.5 hours *
Overcoating interval	min. 8 hours * max. several months *
Full cure after	7 days  (data for components)
Shelf life (cool and dry place)	at least 12 months * see additional data
<b>RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES</b>	<ul style="list-style-type: none"> <li>– <b>for immersion exposure:</b> <ul style="list-style-type: none"> <li>• steel; blast cleaned to SSPC SP10/NACE 2 (ISO-Sa2½), blasting profile (R<sub>z</sub>) 1.6 - 2.8 mils (40 - 70 µm)</li> <li>• steel with approved zinc silicate shop primer; pretreated according to SSPC SP7/NACE 4 (SPSS-Ss)</li> </ul> </li> <li>– <b>for atmospheric exposure conditions:</b> <ul style="list-style-type: none"> <li>• steel with approved zinc silicate shop primer; pretreated according to SPSS or power tool cleaned to SSPC SP3 (SPSS-Pt3)</li> </ul> </li> <li>– substrate temperature should be above 41°F (5°C) and at least 5°F (3°C) above dew point</li> </ul>

# SIGMAZINC 109 HS

(SIGMARITE HS ZINC PRIMER)

March 2007

## INSTRUCTIONS FOR USE

mixing ratio by volume: base to hardener 80 : 20

- the temperature of the mixed base and hardener should preferably be above 59°F (15°C), otherwise extra solvent may be required to obtain application viscosity
- too much solvent results in reduced sag resistance and slower cure
- thinner should be added after mixing the components

Induction time

none

Pot life

8 hours at 68°F (20°C)

## AIRLESS SPRAY

Recommended thinner

Sigma thinner 91-92

Volume of thinner

0 - 15%, depending on required thickness and application conditions

Nozzle orifice

approx. 0.017" - 0.019" inch (= 0.43 - 0.48 mm)

Nozzle pressure

2130 p.s.i. (= approx. 15 MPa; 150 bar)

## CONVENTIONAL SPRAY

Recommended thinner

Sigma thinner 91-92

Volume of thinner

0 - 15%, depending on required thickness and application conditions

Nozzle orifice

0.070" - 0.086" inch (1.8 - 2.2 mm)

Nozzle pressure

43 - 85 p.s.i. (= approx. 0.3 - 0.6 MPa or 3 - 6 bar)

## BRUSH/ROLLER

Recommended thinner

Sigma thinner 91-92

Volume of thinner

0 - 10%

## CLEANING SOLVENT

Sigma thinner 90-53

## SAFETY PRECAUTIONS

for paint and recommended thinners see safety sheets 1430, 1431 and relevant material safety data sheets

this is a solvent based paint and care should be taken to avoid inhalation of spray mist or vapor as well as contact between the wet paint and exposed skin or eyes

## ADDITIONAL DATA

### *Film thickness and spreading rate*

theoretical	447	358	268	179
spreading rate ft <sup>2</sup> /gal (m <sup>2</sup> /l)	(11.0)	(8.8)	(6.6)	(4.4)
dft in mil (µm)	2.4 (60)	3 (75)	4 (100)	6 (150)

# SIGMAZINC 109 HS

(SIGMARITE HS ZINC PRIMER)

March 2007

### Overcoating table for dft 4 mils (100 µm)

substrate temperature	50°F (10°C)	68°F (20°C)	86°F (30°C)	104°F (40°C)
minimum interval	12 hours	8 hours	4 hours	3 hours
maximum interval	3 months when free from zinc salts and contamination			

- zinc rich primers can form zinc salts on the surface; preferably they should not be weathered for long periods before overcoating
- an interval of several months can be allowed under clean **interior** exposure conditions
- in clean exterior conditions, a maximum interval of 3 months can be tolerated, but in industrial or marine conditions this interval should be reduced to the practical minimum
- before overcoating visible surface contamination must be removed by high pressure water cleaning, sweep blasting or mechanical cleaning

### Curing table for dft 4 mils (100 µm)

substrate temperature	touch dry	dry to handle	full cure
50°F (10°C)	5 hours	6 hours	20 days
59°F (15°C)	3 hours	4 hours	10 days
68°F (20°C)	2.5 hours	3 hours	7 days
86°F (30°C)	1 hour	1.5 hour	5 days

- SigmaZinc 109 HS can be applied at temperatures between 40°F (5°C) and 50°F (10°C), but the curing rate will be very slow
- for such applications alternative zinc rich primers are recommended: SigmaZinc 19, SigmaZinc 158 and SigmaZinc 160 for systems exposed to atmospheric conditions, SigmaGuard 750 for systems exposed to immersed conditions
- adequate ventilation must be maintained during application and curing (please refer to sheet 1433 and 1434)

### Worldwide availability

Whilst it is always the aim of SigmaKalon Marine & Protective Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/ circumstances.

Under these circumstances an alternative product data sheet is used.

# SIGMAZINC 109 HS

(SIGMARITE HS ZINC PRIMER)

March 2007

## REFERENCES

Explanation to product data sheets	see information sheet 1411
Safety indications	see information sheet 1430
Safety in confined spaces and health safety	
Explosion hazard - toxic hazard	see information sheet 1431
Safe working in confined spaces	see information sheet 1433
Directives for ventilation practice	see information sheet 1434
Cleaning of steel and removal of rust	see information sheet 1490

## LIMITATION OF LIABILITY

The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the Sigma Coatings products made by SigmaKalon Marine & Protective Coatings, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. The products and information are designed for users having the requisite knowledge and industrial skills and it is the end-user's responsibility to determine the suitability of the product for its intended use.

SigmaKalon Marine & Protective Coatings has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. SigmaKalon Marine & Protective Coatings therefore does not accept any liability arising from loss, injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise).

The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is therefore the user's responsibility to ensure that this sheet is current prior to using the product.

In the event of any disparity or dispute in the wording of this document, the original English text shall prevail.

PDS 7701  
218766 reddish grey 5010001800