

# WATER & WASTE WATER FACILITIES

SELECT SYSTEM RECOMMENDATION FOR:

OPEN IN NEW WINDOW

\*For best results, print in landscape.

Service	System	Products	Description	Surface Prep. <sup>1</sup>	DFT per Coat	No. of Coats	System DFT Totals	New Construction Product Profile			
								Vol. Solids	VOC	Gloss	Appl. Method
Immersion (Potable)	1	Amercoat 370	Fast-Drying Epoxy	SSPC-SP10	5-6	2	10-12	63%	2.5	Flat	Spray
	1A	Amerlock 2	Fast-Drying Epoxy Mastic	SSPC-SP10	4-6	2	8-12	83%	1.5	Semi	Spray
Immersion (Non-Potable)	2	Amercoat 78HB	Coal-Tar Epoxy	ASTM D-4259/60	16	1	16	78%	1.9	Flat	Spray
Immersion (Non-Potable)	2A	Amerlock 2	Fast-Drying Epoxy Mastic	SSPC-SP10	4-6	2	8-12	83%	1.5	Semi	Spray
Immersion (Severe)	3	Amercoat 90HS	Phenolic Epoxy	SSPC-SP10	4-6	3	12-18	64%	2.7	Flat	Spray
	3A	Amercoat 351	100% Solids Epoxy	ASTM D-4259/60	10-12	2	20-24	100%	0.0	Semi	Spray
Splash/Spill	4	Amerlock 2	Fast-Drying Epoxy Mastic	SSPC-SP6	4-6	2	8-12	83%	1.5	Semi	Spray, brush, roller
Atmospheric Moderate/TD>	5	Amerlock 2	Fast-Drying Epoxy Mastic	SSPC-SP3,6,10	4-6	1	9-11	83%	1.5	Semi	Spray, brush, roller
		Amershield	Aliphatic Polyurethane		5	1		73%	2.2	Gloss	Spray, brush, roller
	5A	Amercoat 385	Multi-Purpose Epoxy	SSPC-SP3,6,10	5-6	1	7-8	66%	2.3	Flat	Spray, brush, roller
		Amercoat 450HS	Aliphatic Polyurethane		2	1		66%	2.4	Gloss	Spray, brush, roller
Atmospheric Severe	6	Amerlock 2 PSX 700	Fast-Drying Epoxy Mastic Engineered Siloxane	SSPC-SP3,6	6-8 3-7	1 1	9-15	83% 90%	1.5 1.0	Semi Gloss	Spray, brush, roller Spray, brush, roller
Atmospheric Mild	7	Amercoat 146	Waterborne Acrylic Primer	SSPC-SP3,6	2-3	1	4-6	40%	0.9	Semi	Spray, brush, roller
		Amercoat 222	Waterborne Acrylic		2-3	1		36%	0.9	Semi	Spray, brush,

			Topcoat									roller
Pipe Exterior(Steel or PVC)	<b>8</b>	<a href="#">Amershield</a>	Aliphatic Polyurethane	SSPC-SP3,6	5	1	5	73%	2.2	Gloss		Spray, brush, roller
Flooring Severe	<b>9</b>	<a href="#">Nu-Klad 105A</a> <a href="#">Nu-Klad 120A</a>	Epoxy Primer Epoxy Surfacer	ASTM D-4259/60	Absorb into concrete 40-175	1 1	40-175	100% 100%	0.0 0.0			Spray,brush,roller Pour and spread
Flooring Moderate	<b>10</b>	<a href="#">Amerlock 2</a>	Fast-Drying Epoxy Mastic	ASTM D-4259/60	8	2	16	83%	1.5	Semi		Spray, brush, roller

**NOTE:** <sup>1</sup> Surface Preparation - Consult SSPC or ASTM Standards. Concrete surface preparation should be ASTM D4259 or D4260

Consult with your Coatings West representative at (866) 691-9601 for complete Ameron information. This chart is designed as a guide. Please refer to product data for specific details.